

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE July 1996	3. REPORT TYPE AND DATES COVERED Final 1 Jun 92 - 31 Mar 96		
4. TITLE AND SUBTITLE Modelling & Observation of Carck Nucleation in Ice Due to Elastic & Plastic Anisotropy		5. FUNDING NUMBERS DAAL03-92-G-0250		
6. AUTHOR(S) Harold J. Frost				
7. PERFORMING ORGANIZATION NAMES(S) AND ADDRESS(ES) Darmouth College Hanover, NH 03755		8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park., NC 27709-2211		10. SPONSORING / MONITORING AGENCY REPORT NUMBER AR028649.4-GS		
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.		12 b. DISTRIBUTION CODE		
13. ABSTRACT (Maximum 200 words) The primary result of this project are a clear understanding of the processes which initial cracks in columnar ice under typical conditions. The primary material of study was laboratory-grown freshwater ice, in which the crystals grew as long columns with diameters in the range of a few millimeters. For some fracture toughness measurements we used large single crystals of freshwater ice. Some related work has also been done on laboratory-grown columnar saline ice.				
14. SUBJECT TERMS		15. NUMBER IF PAGES		
		16. PRICE CODE		
17. SECURITY CLASSIFICATION OR REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

19961021 145

DTIC QUALITY INSPECTED 1

Modelling & Observation of Crack Nucleation
in Ice due to Elastic & Plastic Anisotropy

FINAL REPORT

HAROLD J. FROST

JULY 8, 1996

U.S. ARMY RESEARCH OFFICE

PROJECT NUMBER: 28649-GS

DARTMOUTH COLLEGE

APPROVED FOR PUBLIC RELEASE;

DISTRIBUTION UNLIMITED.

TABLE OF CONTENTS

2. TABLE OF CONTENTS	2
4. REPORT	
A. STATEMENT OF THE PROBLEM STUDIED	3
B. SUMMARY OF THE MOST IMPORTANT RESULTS	3
C. LIST OF ALL PUBLICATIONS AND TECHNICAL REPORTS	5
D. LIST OF ALL PARTICIPATING SCIENTIFIC PERSONNEL	8
5. REPORT OF INVENTIONS	8
6. BIBLIOGRAPHY.	8

4 A. STATEMENT OF THE PROBLEM STUDIED

The primary objective of this research project was to understand the process of crack nucleation in polycrystalline ice. Such crack nucleation, or crack initiation, is necessarily the first step in the brittle compressive failure process in which cracks appear in increasing number, grow, and link up with other cracks to form damage zones which lead to failure. An understanding of how the crack nucleation process depends on the external variables of temperature, stress state, and applied strain rate, and the microstructural variables of grain size and shape and crystallographic orientation, is therefore an underlying contribution to a full understanding of the mechanical strength of ice.

4B. SUMMARY OF IMPORTANT RESULTS

The primary result of this project are a clear understanding of the processes which initial cracks in columnar ice under typical conditions. The primary material of study was laboratory-grown freshwater ice, in which the crystals grew as long columns with diameters in the range of a few millimeters. For some fracture toughness measurements we used large single crystals of freshwater ice. Some related work has also been done on laboratory-grown columnar saline ice. We concentrated on the temperature -10°C , which is the temperature most commonly used to study the behavior of freshwater ice. It is also within the range which is experienced in ice engineering applications. We concentrated on an intermediate range of strain rates (of order 10^{-3} to 10^{-2} s^{-1}) at which ice shows generally brittle behavior (at -10°C). We concentrated on uniaxial compressive loading and biaxial compressive loading. For these conditions we achieved the results described below.

First we have been able to show by numerical evaluations of stress concentrations that the mechanism of crack nucleation at grain corners due to elastic anisotropy is unlikely to operate under any conditions. This is because the elastic constants of ice are sufficiently close to isotropic that the strengths of the stress singularities which occur at grain edges (triple junctions) and corners are not sufficiently strong to generate cracking before reaching stresses near the cohesive strength. (Frost & Gupta, 1993; Picu & Gupta, 1996; Picu, Gupta, & Frost, 1994) Some other stress concentration mechanism must operate. The possibilities include dislocation pile-ups, grain boundary sliding, and second-phase inclusions.

Second we have been able to show that decohesion occurs along grain boundaries when they are subjected to stress states with resolved shear components which promote boundary sliding.

(Picu & Gupta, 1995b) This sliding quickly leads to stress concentrations at the edges of the sliding facets, and these ensuing stress concentrations generate cracks. (Picu & Gupta, 1995a; Picu & Gupta, 1995b) Failure occurs when the crack density reaches a sufficient level.

One of the parameters required to model the initiation of crack extensions is the single crystal fracture toughness or work of fracture. To measure this we undertook experiments for measuring crack propagation in single crystals and bicrystals, using the wedge-opening double cantilever beam geometry. (Chernuschenko, 1995) In these experiments the crack opening displacement was measured as a razor blade wedge was inserted into the mouth of a freshly produced crack of known length. From the crack opening and the geometry one can infer the stress intensity factor at which the crack extended. Some measurements of the critical stress intensity factor required for crack propagation were achieved. We discovered, however, that at our relatively slow crack opening rates, the plastic relaxation process within the ice could lead to misleading results. (Chernuschenko, 1995) Another technique for measuring the inherent cohesive strength of ice is the laser spallation experiment reported by Gupta and Tian (Gupta, Argon, Parks, & Cornie, 1992) This experiment is very similar to the interface adhesion technique described in the next paragraph, but it was done on thin single crystals of ice and the spallation process was a decohesion within the ice itself. From it, cohesive strengths on the order of 1.1 GPa were reported for spallation parallel to the basal plane, and 1.3 GPa (at -10°C) and 1.0 GPa (at -40°C) for spallation parallel to prismatic planes.

As a related topic, we have investigated the removal of ice from structures using the laser spallation technique. Paul Archer (Archer, 1996) performed experiments in which thin ice layers were spalled from aluminum substrates. In this technique the reverse side of the aluminum was subjected to a short laser pulses which generated short compressive stress pulses. These pulses propagated through the aluminum substrate and the adherent layer of ice, to reflect off the ice free surface and return through the ice layer as tensile pulses. If the reflected tensile pulses have sufficient magnitude, when they reach the ice--aluminum interface, they can break the interfacial bond and spall the ice away from the aluminum. Measuring the laser pulse magnitude required to produce spallation therefore measures the interfacial cohesive strength. The magnitude of the stresses generated by the laser pulses could be inferred by measuring the time-dependent surface displacements with a laser interferometer.

To evaluate the effect of temperature, spallation experiments were performed using uncoated, unpolished aluminum substrates at -10° , -20° , -30° , and -40°C . (Archer, 1996) To evaluate the effect of coatings, experiments were performed at -10°C on unpolished aluminum, polished

aluminum, and with one micron thick coatings of polyimide and polymethylmethacrylate (PMMA). For all experiments the interfacial strengths were reported as being close to 180 MPa, except for the experiments on unpolished aluminum at -10°C , for which the strength was about 274 MPa. Reports of these experiments will be published in due course.

4 C. PUBLICATIONS.

Journal Publications

- V. Gupta and X. Tian, 1994, "Measurement of Cleavage Strength in Freshwater Ice Crystals by a Laser Spallation Technique", *Journal of Offshore Mechanics and Arctic Engineering*, **116**, pp. 35-42, 1994.
- V. Gupta and C.R. Picu, 1995 "A Model for the Indentation-Induced Splitting Ice Floe Experiments," *Acta Metallurgica et Materialia* **43**, pp. 1355-1362, 1995.
- C.R. Picu, V. Gupta and H.J. Frost, 1994 "Crack Nucleation Mechanism in Saline Ice", *Journal of Geophysical Research - Solid Earth*, **99**, pp. 11775-11786, 1994.
- C.R. Picu and V. Gupta, 1995a, "Observations of Crack Nucleation in Columnar Ice due to Grain Boundary Sliding", *Acta Metallurgica et Materialia* **43**, 3791-3798, 1995.
- C.R. Picu and V. Gupta, "Crack Nucleation in Columnar Ice due to Elastic Anisotropy and Grain Boundary Sliding", *Acta Metallurgica et Materialia* **43**, 3783-3790, 1995.
- J. Weiss, E.M. Schulson and H.J. Frost, (1996) "The Nucleation of Microcracks in Ice Cubes Compressed Equally on All Boundaries", *Philosophical Magazine A* **73**, 1385, 1996.
- C.R. Picu and V. Gupta, "Stress singularities at triple junctions with freely sliding grains," *International Journal of Solids and Structures* **33**, 1535-1541, 1996.
- C.R. Picu, "Singularities of an Interface Crack Impinging on a Triple Grain Junction", *International Journal of Solids and Structures* **33**, 1563-1573, 1996.
- C.R. Picu and V. Gupta, "Singularities at Grain Triple Junctions in Two-Dimensional Polycrystals with Cubic and Orthotropic Grains", *Journal of Applied Mechanics* **63**, 295-300, 1996.
- C.R. Picu, J. Bergström and V. Gupta, "The brittle failure of columnar ice under off-axis loading", *Scripta Materialia*, in press, 1996.

Conference Papers

- H.J. Frost and T. Smith, 1992, "Crack nucleation in columnar ice", *IAHR 92, Proceedings of the 11th International Symposium on Ice*, Vol. 2, pp. 1075-1086
- V. Gupta, J. Ruhl, G. Kuehn and D. Martinez, 1992, "Preliminary Investigations of the Measurement of Fracture Toughness on Freshwater Ice Crystals and in Bi-crystals", *IAHR*

92 Proceedings of the 11th International Symposium on Ice held at Banff, Alberta, June 15-19, Vol. 3, pp. 1408-1419

- H.J. Frost and V. Gupta, 1993, "Crack Nucleation Mechanisms and Fracture Toughness Measurements in Freshwater Ice", in *Ice Mechanics - 1993* -, edited by J.P. Dempsey, Z.P. Bazant, Y.D.S. Rajapakse, and S. Shyam Sunder, Proceedings of the Ice Mechanics Symposium, First Joint ASCE-EMD, ASME-AMD SES Meeting, June 6-9, 1993, Charlottesville, Virginia, pp. 235-250
- V. Gupta, R.C. Picu and H.J. Frost, 1993, "Crack Nucleation Mechanism in Saline Ice", in *Ice Mechanics - 1993* -, edited by J.P. Dempsey, Z.P. Bazant, Y.D.S. Rajapakse, and S. Shyam Sunder, Proceedings of the Ice Mechanics Symposium, First Joint ASCE-EMD, ASME-AMD SES Meeting, June 6-9, 1993, Charlottesville, Virginia, pp. 199-216.
- V. Gupta and C.R. Picu, 1993, "Size-Effect in Indentation-Induced Splitting Floe Experiments", *Proceedings of the Offshore Mechanics and Arctic Engineering Conference*, Glasgow Scotland, June 20-24, 1993, Vol. 4, pp. 29-34.
- C.R. Picu and V. Gupta, 1994, "Crack nucleation in polycrystalline columnar ice due to anisotropic grains," Proc. IAHR Ice Symposium, Trondheim, Norway.
- H.J. Frost (1995) "Mechanisms of Crack Nucleation in Ice", Joint Applied Mechanics and Materials Summer Conference, June 28-30, 1995, UCLA
- V. Gupta, C.R. Picu and J. S. Bergström (1995) "Nucleation of Splitting Column Cracks in Ice", Joint Applied Mechanics and Materials Summer Conference, June 28-30, 1995, UCLA
- C.R. Picu and V. Gupta (1995) "Grain Boundary Sliding and Crack Nucleation in Freshwater Columnar Ice in the Brittle Deformation Regime", Joint Applied Mechanics and Materials Summer Conference, June 28-30, 1995, UCLA

Theses

- Chernuschenko, M. A., 1995, "Fracture toughness measurements in ice single crystals in double-cantilever beam geometry with the wedge-loaded crack." MS Thesis, Thayer School of Engineering, Dartmouth College, Hanover, New Hampshire, USA, July, 1995.
- Bergström, J. S., 1995, "Crack Nucleation and Final Failure of Freshwater Columnar Ice under Biaxial Compression", MS Thesis, Thayer School of Engineering, Dartmouth College, Hanover, New Hampshire, USA, May, 1995.
- Picu, C. R., 1996, "Stress Concentration and Crack Nucleation in Brittle Materials", Ph.D. Thesis, Thayer School of Engineering, Dartmouth College, Hanover, New Hampshire, USA, June, 1996

Archer, Paul F., 1996, "Investigation of the Adhesion Strength of Ice to Aluminum using a Laser Spallation Experiment", M.S. Thesis, Thayer School of Engineering, Dartmouth College, Hanover, New Hampshire, USA, June, 1996

4 D..SCIENTIFIC PERSONNEL SUPPORTED BY THIS PROJECT AND DEGREES AWARDED

Primary Support:

Harold J. Frost	Principal Investigator
Vijay Gupta	Co-Principal Investigator
Xuefeng Tian	Postdoctoral Research Associate
Jörgen Bergström	Masters of Science Candidate (degree awarded June, 1995)
Maxim Chernuschenko	Masters of Science Candidate (degree awarded June, 1996)
Zhiming Ye	Masters of Science Candidate (degree expected June, 1997)

Temporary Support:

Mark Ralph	Master of Science Candidate (degree awarded June, 1995)
------------	---

Supported by a related ASSERT grant to Prof. Vijay Gupta:

Paul Archer	Masters of Science Candidate (degree awarded June, 1996)
-------------	--

5. REPORT OF INVENTIONS (BY TITLE ONLY): None.

6. BIBLIOGRAPHY

- Archer, P. F. (1996) Investigation of the Adhesion Strength of Ice to Aluminum using a Laser Spallation Experiment. M.S., Dartmouth College.
- Chernuschenko, M. A. (1995) Fracture Toughness Measurements in Ice Single Crystals in Double-Cantilever Beam Geometry with the Wedge-Loaded Crack. M.S., Dartmouth College.
- Frost, H. J., & Gupta, V. (1993). *Crack Nucleation Mechanisms and Fracture Toughness Measurements in Freshwater Ice*. In J. P. Dempsey, Z. P. Bazant, Y. D. S. Rajapakse, & S. S. Sunder (Ed.), Ice Mechanics Symposium, First Joint ASCE-EMD, ASME-AMD, SES Meeting, (pp. 235-250). Charlottesville, Virginia:
- Gupta, V., Argon, A. S., Parks, D. M., & Cornie, J. A. (1992). *Measurement of Interface Strength by a Laser Spallation Technique*. *Journal of Mechanics and Physics of Solids*, Vol. 40 (1), 141-180.

- Picu, R. C., & Gupta, V. (1995a). *Crack Nucleation in Columnar Ice Due to Elastic Anisotropy and Grain Boundary Sliding*. Acta Metallurgica et Materialia, **43**, 3783-3790.
- Picu, R. C., & Gupta, V. (1995b). *Observations of Crack Nucleation in Columnar Ice Due to Grain Boundary Sliding*. Acta Metallurgica et Materialia, **43**, 3791-3798.
- Picu, R. C., & Gupta, V. (1996). *Singularities at grain triple junctions in two dimensional polycrystals with cubic and orthotropic grains*. Journal of Applied Mechanicsin press.
- Picu, R. C., Gupta, V., & Frost, H. J. (1994). *Crack Nucleation Mechanism in Saline Ice*. Journal of Geophysical Research, **99B**, 11775-11786.